
TECHNICAL DATA SHEET
(Additive MFQ-STEAM-ZN)

• **Product Description:**

MFQ-STEAM-ZN prevent from precipitation.
MFQ-STEAM-ZN good thermal stability & weather ability.
MFQ-STEAM-ZN the most important advantage for ZN stabilizer is non-toxic in all PVC heat stabilizers.
MFQ-STEAM-ZN economic property in soft/semi-rigid applications.
MFQ-STEAM-ZN improve products' outdoor property.
MFQ-STEAM-ZN stable in shape-making.

• **General Properties:**

Forms	•Very fine powder
Color	•White

• **Technical Specifications:**

Moisture: Max	0.50	%
Free fatty acid	1.50	%
Melting point	118 – 125	°C
Ash content	12.8 – 14.2	%
Density	1.1	gr/cm ³
Sieve residue at 500 mesh	≤ 1	%
phr	3-5	

ATTENTION

- ✓ **Dosage:** 3% to 5% film depending on final application and thickness.
- ✓ **Lifetime and Storage:** Not to exceed 12-18 months. Keep in cool and dry place under shelter for long periods.

* This product packed in PP Woven bag of 25 kg each