

# DATA SHEET

## Additive MFQ-STEACa



### Product Description

- MFQ-STEACa as most environmental friendly PVC heat stabilizers, it has very good process performances.
- MFQ-STEACa good thermal stability & weather ability.
- MFQ-STEACa anti-severe sunlight, anti-sulfide pollution.
- MFQ-STEACa good compatibility & dispersion with PVC.
- MFQ-STEACa its economic property in soft/semi-rigid applications.

### General Properties

Forms	• Very fine powder
Color	• White

### Technical Specifications

Moisture: Max	• 3	%
Free fatty acid	• 1.00	%
Melting point	• 150 – 160	°C
Ash content	• 9.2– 10.2	%
Density	• 1.08	gr/cm <sup>3</sup>
Sieve residue at 500 mesh	• ≤ 1	%
phr	• 3-5	

### ATTENTION

- **Dosage:** 3% to 5% film depending on final application and thickness.
- **Lifetime and Storage:** Not to exceed 12-18 months. Keep in cool and dry place under shelter for long periods.

\* This product packed in PP Woven bag of 25 kg each

+98-21-77850569  
+98-21-77850591  
+98-21-77850536

811, Eighth Floor, Palmyra Commercial and  
Administrative Complex, Madani Avenue, Western  
Janbazan, Narmak, TEHRAN-IRAN

+98-9916593655

info@marinafq.com

www.marinafq.com